

STYLE 2001

Graphite Yarn, Graphite Filled

CONSTRUCTION:

Style 2001 packing is a rugged premium grade, low friction, high strength, proprietary graphite fiber, twisted together and interlock braided. This style contains a special lubricant to provide a bearing film, and protect shafts from scoring. It also acts as a blocking agent to prevent wicking.

APPLICATION / SERVICE:

Style 2001 packing is ideally suited for use in severe service valves and rotary shaft applications. It handles strong acids and alkali solutions except fuming nitric acid, oleum and fluorine. It can be used to seal steam, water, oil, solvents, alkalis, and acids. It is often used as end rings for packing sets utilizing softer packings that might tend to extrude. This style also handles high temperatures, extremely high shaft speeds (see Service Limits below), most strong chemicals, and reduces shaft wear.

SERVICE LIMITS:

Temperature l	imits	Pressure Limits					
Minimum	-400°F (-240°C)	Static	4350 psi (300 bar)				
Maximum	842°F (450°C)	Reciprocating	1450 psi (100 bar)				
Steam	1202°F (650°C)	Rotating	435 psi (30 bar)				
Shaft Speed	3937 fpm (20m/s)	рН	0-14*				



*except strong oxidizers

APPROXIMATE STANDARD PACKAGE (±10%):

Cino	Ft/Lb	116	65	42.5	24	16.6	12.5	10	8.6	6.7	4.5	3.4	2.7
Size	Inch	1/8	3/16	1/4	5/16	3/8	7/16	1/ 2	9/16	5/8	3/4	7/8	1
Standard Package (±10%)		1 Lb (0.5 Kg) 2 Lbs (1 Kg)		5 Lbs (2 Kg)			10 Lbs (5 Kg)						

Properties and application parameters shown throughout this data sheet are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult TEADIT. Failure to select proper sealing products could result in property damage and/or serious personal injury. Specifications are subject to change without notice; this edition cancels all previous issues.